



类别	性能	剩磁 Br		矫顽力 Hcb		内禀矫顽力 Hcj		最大磁能积 (BH)max		最高工作温度	密度
		T	kGs	kA/m	kOe	kA/m	kOe	kJ/m3	MGOe	°C	g/cm3
Sm1Co5	Sm1Co5-16	0.79-0.84	7.9-8.4	620-660	7.8-8.3	≥1830	≥23	118-135	15-17	≤250	8.3
	Sm1Co5-18	0.84-0.89	8.4-8.9	660-700	8.3-8.8	≥1830	≥23	135-151	17-19	≤250	8.3
	Sm1Co5-20	0.89-0.93	8.9-9.3	684-732	8.6-9.2	≥1830	≥23	150-167	19-21	≤250	8.3
	Sm1Co5-22	0.92-0.96	9.2-9.6	710-756	8.9-9.5	≥1830	≥23	167-183	21-23	≤250	8.3
	Sm1Co5-24	0.96-1.00	9.6-10.0	740-788	9.3-9.9	≥1830	≥23	183-199	23-25	≤250	8.3
Sm2Co17	Sm2Co17-24L	0.95-1.02	9.5-10.2	541-716	6.8-9.0	636-955	8-12	175-191	22-24	≤250	8.4
	Sm2Co17-26L	1.02-1.05	10.2-10.5	541-784	6.8-9.4	636-955	8-12	191-207	24-26	≤250	8.4
	Sm2Co17-28L	1.03-1.08	10.3-10.8	541-764	6.8-9.6	636-955	8-12	207-220	26-28	≤250	8.4
	Sm2Co17-30L	1.08-1.15	10.8-11.5	541-796	6.8-10.0	636-955	8-12	220-240	28-30	≤250	8.4
	Sm2Co17-32L	1.10-1.15	11.0-11.5	541-812	6.8-10.2	636-955	8-12	230-255	29-32	≤250	8.4
	Sm2Co17-26M	1.02-1.05	10.2-10.5	676-780	8.5-9.8	955-1433	12-18	191-207	24-26	≤300	8.4
	Sm2Co17-28M	1.03-1.08	10.3-10.8	676-796	8.5-10.0	955-1433	12-18	207-220	26-28	≤300	8.4
	Sm2Co17-30M	1.08-1.1	10.8-11.0	676-835	8.5-10.5	955-1433	12-18	220-240	28-30	≤300	8.4
	Sm2Co17-32M	1.10-1.13	11.0-11.3	676-852	8.5-10.7	955-1433	12-18	230-255	29-32	≤300	8.4
	Sm2Co17-33M	1.13-1.15	11.3-11.5	820-870	10.3-10.9	955-1433	12-18	246-262	31-32	≤300	8.4
	Sm2Co17-22	0.93-0.97	9.3-9.7	676-740	8.5-9.3	≥1433	≥18	160-183	20-23	≤300	8.4
	Sm2Co17-24	0.95-1.02	9.5-10.2	692-764	8.7-9.6	≥1433	≥18	175-191	22-24	≤300	8.4
	Sm2Co17-26	1.02-1.05	10.2-10.5	748-796	9.4-10.0	≥1433	≥18	191-207	24-26	≤300	8.4
	Sm2Co17-28	1.03-1.08	10.3-10.8	756-812	9.5-10.2	≥1433	≥18	207-220	26-28	≤300	8.4
	Sm2Co17-30	1.08-1.10	10.8-11.0	788-835	9.9-10.5	≥1433	≥18	220-240	28-30	≤300	8.4
	Sm2Co17-32	1.10-1.13	11.0-11.3	812-860	10.2-10.8	≥1433	≥18	230-255	29-32	≤300	8.4
	Sm2Co17-33	1.13-1.15	11.3-11.5	820-870	10.3-10.9	≥1433	≥18	246-262	31-32	≤300	8.4
	Sm2Co17-24H	0.95-1.02	9.5-10.2	692-764	8.7-9.6	≥1990	≥25	175-191	22-24	≤350	8.4
	Sm2Co17-26H	1.02-1.05	10.2-10.5	748-796	9.4-10.0	≥1990	≥25	191-207	24-26	≤350	8.4
	Sm2Co17-28H	1.03-1.08	10.3-10.8	756-812	9.5-10.2	≥1990	≥25	207-220	26-28	≤350	8.4
	Sm2Co17-30H	1.08-1.10	10.8-11.0	788-835	9.9-10.5	≥1990	≥25	220-240	28-30	≤350	8.4
	Sm2Co17-32H	1.10-1.13	11.0-11.3	812-860	10.2-10.8	≥1990	≥25	230-255	29-32	≤350	8.4
	Sm2Co17-33H	1.13-1.15	11.3-11.5	830-880	10.4-11	≥1990	≥25	246-262	31-32	≤350	8.4